

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 5 A61K 9/16, 9/22, A61L 27/00	A1	(11) International Publication Number: WO 92/03125 (43) International Publication Date: 5 March 1992 (05.03.92)
(21) International Application Number: PCT/US91/04147 (22) International Filing Date: 19 June 1991 (19.06.91) (30) Priority data: 567,424 14 August 1990 (14.08.90) US (71) Applicant: PFIZER HOSPITAL PRODUCTS GROUP, INC. [US/US]; 235 East 42nd Street, New York, NY 10017 (US). (72) Inventors: BAO, Qi-Bin ; 30 Washington Court, Livingston, NJ 07039 (US). DUMBLETON, John, H. ; 512 East Saddle River Road, Ridgewood, NJ 07450 (US). HIGHAM, Paul, A. ; 27 Bearfort Terrace, Ringwood, NJ 07456 (US).		(74) Agents: RICHARDSON, Peter, C. et al.; Pfizer Inc., Patent Department, 235 East 42nd Street, New York, NY 10017 (US). (81) Designated States: AT (European patent), AU, BE (European patent), CA, CH (European patent), DE (European patent), DK (European patent), ES (European patent), FR (European patent), GB (European patent), GR (European patent), IT (European patent), JP, KR, LU (European patent), NL (European patent), SE (European patent). Published <i>With international search report.</i>
(54) Title: BONE GROWTH STIMULATOR (57) Abstract An implantable material for promoting bone growth has a microporous structure exhibiting an average pore size of at least 30 Å. The porous biomaterial is capable of retaining macromolecules having a molecular weight of at least 15,000 and up to 500,000.		

USSN 09/421,545
Atty docket #432722002621

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MG	Madagascar
AU	Australia	FI	Finland	ML	Mali
BB	Barbados	FR	France	MN	Mongolia
BE	Belgium	GA	Gabon	MR	Mauritania
BF	Burkina Faso	GB	United Kingdom	MW	Malawi
BG	Bulgaria	GN	Guinea	NL	Netherlands
BJ	Benin	GR	Greece	NO	Norway
BR	Brazil	HU	Hungary	PL	Poland
CA	Canada	IT	Italy	RO	Romania
CF	Central African Republic	JP	Japan	SD	Sudan
CG	Congo	KP	Democratic People's Republic of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SN	Senegal
CI	Côte d'Ivoire	LI	Liechtenstein	SU ⁺	Soviet Union
CM	Cameroon	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TC	Togo
DE ⁺	Germany	MC	Monaco	US	United States of America
DK	Denmark				

⁺ Any designation of "SU" has effect in the Russian Federation. It is not yet known whether any such designation has effect in other States of the former Soviet Union.

BONE GROWTH STIMULATORBACKGROUND OF THE INVENTION

5

Field of the Invention

This invention relates to bone growth stimulation.

- 10 More particularly, the invention relates to the use of dextran beads having a controlled pore size to stimulate bone and tissue growth.

Description of the Prior Art

15

- In recent years, substantial research work on induced bone growth or osteogenesis has been conducted due to its clinical significance. Among all the different efforts, two separate but related approaches have brought most attention either because of their success in solving orthopedic problems or because of their considerable interest in the biology and applied science of osteo-induction. The first consists of clinical investigations of electric effect on inducing new bone formation. The second consists of biochemical investigations into bone growth, coupling, osteogenesis factors and a bone morpho-genetic protein fraction.

- The first approach, which has been documented at least a century ago, is to apply an electric field to stimulate and regulate osteogenesis. During the last forty years, more reports have shown that the cathode stimulates osteo-inductive activity in both animal tests and clinical cases. Several studies have revealed that certain materials, such as neurones, myoblasts, neutral crest cells, epithelial cells, fibroblasts and osteoblasts migrate towards the cathode in the electric field. It could be one or a group of these materials, or some other unidentified materials, that play an important role in the process of bone regeneration.
- 40

-2-

that play an important role in the process of bone regeneration.

The second approach, which started at a later time but has gained considerable attention recently, concentrates on identifying and isolating osteoinduction factors. Bone morphogenetic protein and human skeletal growth factor are the two osteoinductive proteins which have been isolated and characterized. Studies have shown that implantation of these proteins foster new bone formation.

More recently, researchers have applied charged dextran beads to enhance new bone formation. The unique characters of the dextran charged beads, their large porosity, large surface area, different charged groups and their affinity to different proteins have given some promising results. These results were reported at the 24th Annual Meeting of the Orthopaedic Research Society between February 1 and 4, 1988 and published in the article "Charged Beads: Generation of Bone and Giant Cells" in the Journal of Bone & Mineral Research, 1988.

In the prior art study, three different types of Sephadex dextran beads made by Pharmacia, Inc. were used without any pre-treatment. These beads are made from polyglucose dextran cross-linked with epichlorohydrin. The charged groups for producing the negative or positive charge are attached to glucose units in the matrix by stable ether linkages. The beads were suspended in Tyrode's salt solution (buffered at pH=7.3) and UV sterilized. The chemical and physical properties of these beads are listed in Table 1. The "fractionation range" refers to the ability of the beads to separate proteins having the stated molecular weights (MW).

-3-

TABLE 1

		Bead		Counter	Fractionation
	<u>Bead</u>	<u>Charge</u>	<u>Charge Group</u>	<u>Ion</u>	<u>Range (MW)</u> <u>Globular Proteins</u>
5	G-25	No	Neutral	No	1000-5000
	DEA-A-25	Positive	Weak Base Diethylaminoethyl	Cl ⁻	<30000
10	CM-C-25	Negative	Weak Acid Carboxymethyl	Na ⁺	<30000

15

In this study, only the negatively charged CM-C-25 beads displayed an osteoinductive effect. The study concluded that the negative electrical charge stimulated bone growth.

20 Use of charged beads to promote new bone formation may stem from one or both of the electric field inducing effect and the osteoinductive factors effect. Although quite a few studies have been conducted to investigate the effect of surface charge of the biomaterials on the bioactivity, 25 very little effort has been taken in the study of the porosity effect of the biomaterials in the osteogenesis process.

Biomaterials with osteoinductive activity can be used not only to promote the healing of defective or fractured 30 bone, but also to improve the integration of an existing implant with the surrounding tissue if the existing implant is coated with the bioactive materials. For the latter application, an interfacial bond of biomaterial with adjacent tissue will be the key issue to the success of 35 implantation.

In order to understand the mechanism of biomaterial induced osteogenesis, a brief consideration of bone structure is essential. Bone is a specialized connective tissue comprising cells and an extracellular matrix (ECM). 40 One type of cell, the osteoblast, is responsible for the fabrication of ECM. The ECM comprises organic and

-4-

inorganic components. The organic component which weighs about 35% of the total weight is composed predominantly (95%) of Type I collagen. The remainder (5%) is a complex mixture of non-collagenous proteins and other macromolecules. Among these proteins, several of them, such as Bone Morphogenetic Protein (BMP), human Skeletal Growth Factor (hSGF) and some other growth factors, are known to increase cell replication and have important effects on differentiated cell function. However, little is understood of the precise modes of action of these macromolecules. The inorganic component of bone ECM is a complex calcium hydroxyapatite, more complex than the stoichiometric formula for hydroxyapatite, $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$, would suggest.

Due to the important role that osteoblasts and some osteoinductive factors play in the osteogenesis process, it is the hope that any biomaterials applied will have the capability either to colonize and concentrate the osteoinductive macromolecules, or to let the osteoblasts migrate towards the surface of these biomaterials. The unique properties of dextran beads have made them a good candidate for an osteoinductive material.

First, charging the beads offers an electric environment in the body when implanted, the same effect as an electrode can offer. Second, the different charged group and different porosity of the beads makes it possible to selectively bind to certain proteins with specific molecular weight and charge. Charged beads have been employed to separate proteins based on their different molecular weight and affinity to the beads. This characteristic, if the correct bead is chosen, makes it possible for the bead to bind and concentrate certain osteoinductive factors near the beads.

The actual osteogenesis induced by biomaterials is a complex and regulated process and the exact mechanism of it is, at the moment, not well understood. Several hypotheses have been proposed trying to correlate the in vivo/in-vitro results with the biomaterial properties, such as steric

-5-

charge, porosity, particle size and the nature of the materials, etc. Among all these hypotheses, one leans its explanation more to the interaction between the biomaterials and the osteoinductive factors, which include

5 Bone Morphogenetic Protein (BMP), human Skeletal Growth Factor (hSGF) and some other growth factors. The interaction could actually result in colonizing, concentrating and finally activating the osteoinductive factors involved. It has been known that some biological molecules, BMP in

10 particular, are responsible for inducing the new bone formation. Another hypothesis emphasizes more the interaction of the biomaterials and bone cells, particularly osteoblasts, which are responsible for the fabrication of the ECM. It has been found in vitro that osteoblasts

15 migrate towards different biomaterials at different rates and attach onto them with different morphologies depending on the surface charge of the biomaterials. However, the correlation of bone cell morphology and the osteoinductive activity is still not clear. It is also not understood

20 that if the different cell morphology is the direct effect of the surface charge or if the effect is indirect. Due to the fact that the rate of cell migration towards the biomaterials is much slower than the rate of chemical or steric charge interaction between the macromolecules or

25 other organic or inorganic chemicals in the physiological environment and the biomaterials, the surface charge of the biomaterials could be altered before the cells migrate and attach to the biomaterials.

In the prior art, the investigation has been only

30 concentrated on the charge effect. It has indeed been found that osteoblast migratory morphology and extracellular matrix synthesis are sensitive to the charge of the biomaterial which is colonized. Very little attention has been paid to the effect of the porosity of the biomaterial used either as implants or as a coating on the metal

35 implants. Because it has been known that osteoblasts colonizing a biomaterial are able to span pore openings on

the surface of macroporous, bioactive substrates and the fact that the dimension of the osteoblasts is much bigger than that of the porosity studied in this art, the porosity of the beads investigated in this art probably would have little direct effect on the osteoblast migratory morphology. However, the indirect effect on osteoblast migratory morphology, which is caused by the fact that various macromolecules have different binding capability to the different pore size beads, is still possible. Because most osteoinductive macromolecules have the molecular weight range between 15,000 to 30,000, the porosity of the biomaterials used in the implants will have significant effect on the binding capability of these osteoinductive macromolecules.

The porosity of the dextran beads depends on the degree of cross-linking and the concentration of the charged groups attached to them. Sephadex A and C type beads are derived from the G-type beads by introducing the charged groups to the matrix. Although the numbers of A and C beads still remain the same as the G bead (A-25 and C-25 are made from G-25, A-50 and C-50 are made from G-50), the porosities of wet beads change significantly due to the increase of swelling capability by introducing the charged groups. Each Sephadex bead has a different molecular weight range over which molecules can be fractionated. Molecules with molecular weight above the upper limit of this range, the exclusion limit, are totally excluded from the gel. Table 2 gives the fractionation ranges for the different Sephadex dextran beads.

-7-

TABLE 2

PROPERTIES OF SEPHADEX

5				
Fractionation Range (MW)				
10	Sephadex Type	Peptides and Globular		Bed
		Proteins	Dextrans	Volume ml/g dry Sephadex
	G-25	1000-5000	100-5000	4-6
15	G-50	1500-30000	500-10000	9-11
	G-75	3000-80000	1000-50000	12-15
	G-100	4000-150000	1000-100000	15-20
20	A-25, C-25	<30000		7-10
	A-50, C-50	30000-150000		vary with pH
25				

While dextran beads have been discussed, other polymers having properties similar to those shown above can be used. For example, an entire orthopedic implant can be made of such polymers (with the above properties) or an existing orthopedic implant can be coated with such polymers to form an osteoinductive surface thereon.

35

SUMMARY OF THE INVENTION

It is an object of this invention to provide an implantable material for promoting bone growth.

It is a further object of this invention to provide an implantable material which has a porous structure with a pore size capable of retaining molecules of osteoinductive proteins therein.

It is yet another object of this invention to provide an implantable material which can be used as a carrier for osteoinductive factors.

-8-

These and other objects are achieved by an implantable biomaterial having a porous surface exhibiting an average pore size of at least 30 Å. This pore size is capable of retaining molecules having a molecular weight of at least 15,000 and up to 500,000. At the high end of the molecular weight range, the average pore size is about 500 Å. Dextran beads exhibit this porosity and may be used as the biomaterial. Clearly, other polymers having similar pore sizes and capable of retaining molecules with the range stated above can also be used.

This biomaterial having a porous surface is used to determine the osteoinductive characteristics of materials as they relate to the ability of the material to bind osteoinductive macromolecules. The materials are either uncharged, negatively charged or positively charged.

This biomaterial may be Sephadex type dextran beads as indicated above. All beads having a pore size capable of binding with macromolecules with a molecular weight of more than 5000 showed osteoinductive capabilities. This was true regardless of charge.

The biomaterial may be modified to carry osteoinductive factors by impregnating the biomaterial with osteoinductive factors by placing it in a solution or slurry containing these factors prior to implantation. Alternatively, the biomaterial may be directly implanted at a bony site where the porous biomaterial will bond and inherently act to concentrate the osteoinductive factors.

The porous biomaterial which acts to promote bone growth can be formed into and used as an implantable device. The biomaterial can also be used as a coating material for an existing implantable device without altering the bulk properties of the original device. The osteoinductive characteristic of the porous biomaterial not only can promote the healing of defective or fractured bone but also can improve the fixation of an existing implant by being used as a coating on the same.

DESCRIPTION OF THE PREFERRED EMBODIMENT

The invention will now be described in further detail
 5 with reference being made to the following example. It
 should be recognized, however, that the example is given as
 being illustrative of the present invention and is not
 intended to define or limit the spirit and scope thereof.

10

Example

Two neutral dextran beads (G-25 and G-75) with
 different pore size purchased from Pharmacia were used.
 The beads were washed with 0.1N NaOH to remove any impur-
 ities then balanced with pH buffer. Sterilization took
 15 place by autoclaving the beads at 120°C for 30 minutes.
 The chemical and physical properties of these two beads,
 along with the two charged beads, are listed in Table 3.

TABLE 3

20

	<u>Bead</u>	<u>Bead Charge</u>	<u>Charge Group</u>	<u>Counter Ion</u>	<u>Fractionation Range (MW) Globular Proteins</u>
25	G-25	No	Neutral	No	1000-5000
	G-75	No	Neutral	No	3000-80000
30	DEAE-A-25	Positive	Weak Base Diethylaminoethyl	Cl ⁻	<30000
	CM-C-25	Negative	Weak Acid Carboxymethyl	Na ⁺	<30000

35

A 6.0mm hole was drilled into the distal femoral
 40 epiphysis of eighteen rabbits. The hole was drilled from
 the medial surface toward, but not extending through, the
 lateral surface. The right limb of each animal was used as
 a control and the defect filled with neutral charged

-10-

dextran beads (G-25). The left drill hole was filled with the neutral beads with a larger pore, G-75.

The materials were implanted for four weeks, at which time the animals were sacrificed. The condyles of each limb were cut into lateral and medial halves. The medial and lateral halves of each femur was decalcified and embedded in methylmethacrylate. A histological examination was performed and the results are shown in Table 4.

10

TABLE 4

HISTOLOGY RESULTS

15

<u>Bead Injected</u>	<u>Tissue Ingrowth*</u>	<u>Number of Sections Examined</u>
G-25, Uncharged	.	6
G-75, Uncharged with Large Pore Size	+	2

20

25

., only soft tissue ingrowth

+, good to excellent bone ingrowth

30

35

40

From the prior art data, it is very easy to conclude that it is necessary to have electric charged group in the beads for osteoinductive activity. However, if the physical properties of the different beads are examined in view of the results of Example 1, it is found that this conclusion is probably incorrect. It is very easy to assume that G-25 beads would have the same pore size as the A-25 and C-25 beads because all A-25 and C-25 beads are derived from G-25 beads by attaching the charged groups to them and because they have the same cross-link density. However, the actual pore size of wet G-25 beads is quite different from that of A-25 and C-25 beads, as we can see from Table 2, because attaching the charged groups to the polymer increases the swell capability of the beads. The

-11-

fractionation range for G-25 is only 1000 to 5000, while the fractionation range for both A-25 and C-25 is up to 30,000. It is improper, therefore, to use G-25 beads as a control to compare them with A-25 and C-25 beads for electric charge effect because there is something (porosity) other than electric charge which is also very different among these beads. It is not surprising that the G-25 beads did not have any osteoinductive activity in the prior art because most, if not all, osteoinductive proteins have a molecular weight larger than 5000.

Due to the significant porosity difference among these charged and uncharged -25 beads, G-75 beads, which have the same order of pore size as A-25 and C-25 beads, were chosen to see how significantly the porosity contributes to the osteoinductive process. In this case, we can differentiate the pore size effect from the electric charge effect. Because G-25 and G-75 beads are made of the same polymer, any difference observed in osteoinductive activity should be attributed to the pore size effect. At the same time, the result of G-75 beads also can be used to compare with those beads used in the prior art to see how the different bead charges affect the osteogenesis.

The present study demonstrated that significant bead-associated new bone formation was observed with the uncharged G-75 beads, while there was no evidence of bead-associated new bone with the uncharged G-25 beads. This indicates that the microporosity plays a very important role in the biomaterial induced osteogenesis process. This invention, however, does not intend to indicate that microporosity is the only requirement of the osteoinductive activity for a biomaterial. The capability of interaction between the biomaterial and the molecules and living cells is still very important. It is very difficult to use steric charge effect to explain the binding between the neutral or positively charged dextran beads and the charged osteoinductive factors. However, other intermolecular forces including dipole forces, hydrogen bonds and hydro-

-12-

phobic bonds are still available for the interaction between the biomaterials and the osteoinductive factors and living cells. The present study shows that the appropriate microporosity of a biomaterial, either used alone or used
5 as a coating, can promote osteoinductive activity of the material.

Because most known biologically active macromolecules in ECM have a molecular weight between 15,000 to 30,000, with the exception of hSGF with a molecular weight of
10 around 80,000, it will be expected that the minimum average microporosity should be large enough to accommodate those macromolecules. The upper limit of the microporosity would have less restriction than the low limit in binding these macromolecules. Although only one large porosity dextran
15 bead (G-75) was used, based on the knowledge of basic biochemistry and biology, a conclusion can be extrapolated that the appropriate pore size for a bioactive material in the osteogenetic applications should have the molecular fractionation range of MW 15,000 to 500,000, which
20 corresponds approximately to the size of between 30Å and 500Å

While several embodiments and examples of the present invention have been described, it is obvious that many changes and modifications may be made thereunto, without
25 departing from the spirit and scope of the invention.

CLAIMS:

1. An implantable material for promoting bone growth comprising:

a biomaterial having a microporous structure
5 exhibiting an average pore size of at least 30Å, said biomaterial capable of retaining in said pores molecules having a molecular weight of at least 15,000 and up to 500,000.

2. The implantable material as set forth in Claim 1
10 wherein the biomaterial is a wetted dextran bead.

3. The implantable material as set forth in Claim 1 wherein said average pore size is less than 500Å.

4. The implantable material as set forth in Claim 1 wherein said molecules contain osteoinductive factors.

15 5. An implantable material for stimulating and promoting bone growth comprising:

a multiplicity of uncharged dextran beads having, in the wet state, a microporous structure exhibiting an average pore size of at least 30Å, said beads capable of
20 retaining in said pores molecules having a molecular weight of between 15,000 and 500,000.

6. The implantable material as set forth in Claim 5 wherein said molecules contain osteoinductive factors.

7. A process for promoting tissue growth around a
25 prosthetic implant comprising:

coating the prosthetic implant with a biomaterial having a microporous structure exhibiting an average pore size of at least 30Å, said biomaterial capable of retaining in said pores molecules having a molecular weight of at
30 least 15,000 and up to 500,000; and

implanting said prosthetic implant within the body adjacent the tissue.

8. The process as set forth in claim 1 wherein the biomaterial is a wetted dextran bead.

35 9. The process as set forth in claim 1 wherein the average pore size is less than 500Å.

-14-

10. The process as set forth in claim 1 wherein the molecules contain osteoinductive factors.

11. A process for promoting tissue growth comprising:
forming a prosthetic implant from a multiplicity of
5 uncharged dextran beads having, in the wet state, a micro-
porous structure exhibiting an average pore size of at
least 30Å, said beads capable of retaining in said pores
molecules having a molecular weight of between 15,000 and
500,000;
10 implanting said prosthetic implant within the body
adjacent the tissue.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 91/04147

I. CLASSIFICATION OF SUBJECT MATTER (If several classification symbols apply, indicate all)⁶

According to International Patent Classification (IPC) or to both National Classification and IPC

Int.Cl.5 A 61 K 9/16 A 61 K 9/22 A 61 L 27/00

II. FIELDS SEARCHED

Minimum Documentation Searched⁷

Classification System

Classification Symbols

Int.Cl.5

A 61 K

A 61 L

Documentation Searched other than Minimum Documentation
to the Extent that such Documents are Included in the Fields Searched⁸III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹Category¹⁰ Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹² Relevant to Claim No.¹³

X

WO,A,9001955 (ED GEISTLICH SOHNE) 8
March 1990, see claims 1,2,5,7,9,18-21; page 3,
lines 33-38; page 4, lines 15-32; page 6, lines
20-35; page 1, example 4
---1,2,4-7
,10,11

P,X

US,A,4988358 (B.L. EPPLEY) 29
January 1991, see claims; column 7, lines 41-63
---1,2,4,7
,10-11

A

EP,A,0058867 (MUNDIPHARMA) 1
September 1982, see claims; page 4, lines 14-17

1,5,7

¹⁰ Special categories of cited documents :^{"A"} document defining the general state of the art which is not
considered to be of particular relevance^{"E"} earlier document but published on or after the international
filing date^{"L"} document which may throw doubts on priority claim(s) or
which is cited to establish the publication date of another
citation or other special reason (as specified)^{"O"} document referring to an oral disclosure, use, exhibition or
other means^{"P"} document published prior to the international filing date but
later than the priority date claimed^{"T"} later document published after the international filing date
or priority date and not in conflict with the application but
cited to understand the principle or theory underlying the
invention^{"X"} document of particular relevance; the claimed invention
cannot be considered novel or cannot be considered to
involve an inventive step^{"Y"} document of particular relevance; the claimed invention
cannot be considered to involve an inventive step when the
document is combined with one or more other such docu-
ments, such combination being obvious to a person skilled
in the art.^{"&"} document member of the same patent family

IV. CERTIFICATION

Date of the Actual Completion of the International Search

18-11-1991

Date of Mailing of this International Search Report

11.12.91

International Searching Authority

EUROPEAN PATENT OFFICE

Signature of Authorized Officer

N. DE BIE



Form PCT/ISA/210 (second sheet) (January 1985)

FURTHER INFORMATION CONTINUED FROM THE SECOND SHEET

V. ☒ OBSERVATION WHERE CERTAIN CLAIMS WERE FOUND UNSEARCHABLE ¹

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☒ Claim numbers
Authority, namely: because they relate to subject matter not required to be searched by this
Although claims 7-11 are directed to a method of treatment
of the human body by therapy the search has been carried out
and based on the alleged effects of the compounds
2. ☐ Claim numbers
with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically. because they relate to parts of the international application that do not comply
3. ☐ Claim numbers
the second and third sentences of PCT Rule 6.4(a). because they are dependent claims and are not drafted in accordance with

VI. ☐ OBSERVATIONS WHERE UNITY OF INVENTION IS LACKING ²

This International Searching Authority found multiple inventions in this international application as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims of the international application
2. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims of the international application for which fees were paid, specifically claims:
3. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claim numbers:
4. ☐ As all searchable claims could be searched without effort justifying an additional fee, the International Searching Authority did not invite payment of any additional fee.

Remark on Protest

- ☐ The additional search fees were accompanied by applicant's protest.
☐ No protest accompanied the payment of additional search fees.

**ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO.**

US 9104147
SA 50691

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.
The members are as contained in the European Patent Office EDP file on 06/12/91
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A- 9001955	08-03-90	None	
US-A- 4988358	29-01-91	None	
EP-A- 0058867	01-09-82	DE-A- 3106445	04-11-82
		DE-A- 3126273	20-01-83
		DE-A- 3133015	10-03-83
		DE-A- 3133016	10-03-83
		CA-A- 1195615	22-10-85
		US-A- 4610692	09-09-86

EPO FORM P0029

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82